

WELL CONSTRUCTION
COLLINS 76-17

Drill 17-1/2" hole to 1895'

Ran 13-3/8" 54.5#/ft. K-55 buttress thread casing to 1895'. Cement from 1895' to surface with Class "G" cement, 1:1 perlite and 40% silica flour.

Drill 12-1/4" hole to 5955'. Ran 9-5/8" 43-1/2 #/ft. N-80 buttress thread casing to 5823'. Cement from 5955' to surface with Class "G" cement, 50#/sack spherelite, 40% silica flour.

Drill 8-1/2" hole from 5955' to 9005'.